

# **INDUSTRIAL TRANSFORMER OIL**



Technical Data Sheet

# **ELPRIMO BS 148 TRANSFORMER OIL (UN-INHIBITED)**

#### Performance Standards:

As per BS-148 1984 CLASS 1 /IEC 296 CLASSI - Uninhibited

#### **Product Specifications:**

| CHARACTERISTICS   | TEST METHOD          | SPECIFICATION                                   | TEST RESULTS                                 |
|---|----------------------|---|--|
| A - Physical Properties   | -148 /1984           |   |  |
| APPEARANCE  | 7.1                  | Clear, free from sediment<br>& suspended matter | Clear, free from sediment & suspended matter |
| Density@29.5 o C, kg/dm3<br>Density@20o C, kg/dm3                               | 7.2                  | TBR   | TBR<br>TBR                                   |
| Kinematic Viscosity, mm2/s<br>at 40 o C<br>at – 15 o C                          | 7.3                  | < 16.5<br>< 800                                 | 8.86<br>245.38                               |
| Flash Point (PMCC), o C   | 7.4                  | > 140   | 150  |
| Pour Point, o C   | 7.5                  | <=-30   | -45  |
| Interfacial tension, N/m @ 25 o C   | 7.6                  | > 0.040   | 0.046  |
| B- Electricals Properties   |                      |   |  |
| Electric strength<br>(Break down voltage)<br>KV As delivered<br>After Treatment | 7.12                 | > 30 KV<br>> 50 KV                              | 70<br>-                                      |
| Dielectric dissipation factor @ 90 o C & 40HZ-60HZ                              | 7.13                 | < 0.005   | 0.0004                                       |
| C- Chemicals Properties   |                      |   |  |
| Neutralization Value, mg KOH/g.   | 7.7                  | < 0.03  | 0.0002                                       |
| Corrosive Sulphur   | 7.8                  | Non-Corrosive                                   | Non-Corrosive                                |
| Water content, ppm  | 7.9                  | < 40  | 12   |
| Antioxidant additives, %  | 7.10                 | Absent  | Absent                                       |
| Oxidation Stability (164 hours)   |                      |   |  |
| Neutralization Value, mg. KOH/g<br>Sludge, % by Mass                            | 11.07.1 / Appendix A | < 0.40<br>< 0.10                                | 0.086<br>0.005 %                             |

# DISCLAIMER:

The test data provided is not a final specification; rather, it serves as a guideline and may vary within acceptable production tolerances. Bravoil reserves the right to modify this test data. Any updates will supersede previous versions, so please refer to the most recent Technical Data Sheet (TDS).

## **HEALTH & SAFETY, ENVIRONMENT:**

Prolonged and repeated contact with oil may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used oil in to drains or the environment. Dispose to an authorized used oil collection point. For further information on Safety Guidelines please refer to MSDS available on our website www.bravoil.ae

### **HEALTH & SAFETY:**

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet www.bravoil.ae

#### DEOTECT THE ENVIRONMENT.

Take used oil to an authorized collection point. Comply with local regulation. Do not discharge into drains, soil or water.

#### STORAGE:

We recommend to store all packages under cover. In case outside storage is unavoidable, drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should never be stored above  $60^{\circ}$ C, exposed to hot sun or freezing conditions.