

# **INDUSTRIAL HYDRAULIC FLUID**

**Technical Data Sheet** 

# HYDRON SYN HVLP

## PRODUCT DESCRIPTION:

HYDRON SYN HVLP hydraulic oils are synthetic oils designed with exceptional high-temperature performance and shear stability, along with excellent oxidation resistance. Their high viscosity index and low pour point allow for use over a broad temperature range. These oils offer superior wear protection, thermal stability at elevated temperatures, reduced deposit formation, and extended service life. They safeguard hydraulic system components from rust and corrosion, formulated for very long drain intervals, providing equipment protection lasting up to three times longer than conventional products.

### APPLICATION:

- Hydraulic systems such as Numerically Controlled (NC) machines
- Systems employing multi-metal component designs
- High pressure vane, piston and gear pumps
- · Systems where cold start-up and / or very high operating

# FEATURES & BENEFITS:

- Helps extend service intervals
- Helps prevent internal hydraulic system corrosion
- Helps reduce wear of components
- Helps to ensure equipment protection at cold start-up temperatures

# PERFORMANCE LEVELS: Meets or Exceeds:

- DIN 51524 Part 3, Type HVLP
- Denison HF-0, HF-1, HF-2

temperatures are typical

- In systems containing gears and bearings
- Systems requiring a high degree of loaDcarrying capability and anti-wear protection

BRAVOI

- Helps protect system components at high operating temperatures
- Helps reduce system deposits and potential sludging
- Excellent air release

# TYPICAL PROPERTIES:

PARAMETERS	TEST METHOD	UNIT	HYDRON SYN HVLP			
ISO VG			32	46	68	100
Kinematic Viscosity @ 104°F /40°C	ASTM D7042	cSt	32	46	68	100
Kinematic Viscosity @ 212°F /100°C	ASTM D7042	cSt	6.55	8.33	11.24	15.3
Viscosity Index (min)	ASTM D2270	-	148	157	158	161
Density @15°C/ 60°F	ASTM D4052	g/cm <sup>3</sup>	TBR	TBR	TBR	TBR
Flash Point (min)	ASTM D92	°C	236	251	260	260
Pour Point (max)	ASTM D97	°C	-51	-57	-54	-54
Copper Strip Corrosion 3 hours @ 100° C	ASTM D130	-	1B	1B	1B	1B
Rust Characteristics	ASTM D665B	-	Pass	Pass	Pass	Pass
Foam Sequence I, II, III	ASTM - D892	ml	0/0	0/0	0/0	0/0
Demulsibility, 54°C, 3ml emulsion	ASTM - D1401	minutes	15	15	15	-

#### DISCLAIMER:

The test data provided is not a final specification; rather, it serves as a guideline and may vary within acceptable production tolerances. Bravoil reserves the right to modify this test data. Any updates will supersede previous versions, so please refer to the most recent Technical Data Sheet (TDS).

## HEALTH & SAFETY, ENVIRONMENT:

Prolonged and repeated contact with oil may cause skin disorders. Avoid contact. Wash immediately with soap and water. Do not discharge used oil in to drains or the environment. Dispose to an authorized used oil collection point. For further information on Safety Guidelines please refer to MSDS available on our website www.bravoil.ae

#### HEALTH & SAFETY

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office or via the internet www.bravoil.ae

### PROTECT THE ENVIRONMENT:

Take used oil to an authorized collection point. Comply with local regulation. Do not discharge into drains, soil or water.

### STORAGE:

We recommend to store all packages under cover. In case outside storage is unavoidable, drums should be laid horizontally to avoid the possible ingress of water and damage to drum markings. Products should never be stored above 60°C, exposed to hot sun or freezing conditions.

